

# 3M™ Scotchkote™ Urethane Elastomer 80FG 532

(Formerly known as Flexi-Tech 80 FG)

## Data Sheet and Application Guide

### Product Description

Scotchkote Urethane Elastomer 80FG 532 has been specifically developed as an elastomeric system with a high degree of flexibility for casting and moulding rubber components.

### Product Features

- Properties similar to factory produced rubbers.
- Designed for moulding and casting of flexible components.
- Designed for use to resurface impellers, chutes, and hoppers.

### Surface Preparation

Heavy contamination due to oil or grease must be removed using a suitable degreasing agent. If your local air quality regulations allows its use, we recommend using 3M Scotchkote Universal Cleaner 020.

Any areas of frayed or fragmented rubber should be cut away to provide a sound repair area. Smooth surfaces, including metals, should be mechanically etched to produce a good profile, with abrasive blasting being preferred for metal substrates. Rubber surfaces are best roughened using a stiff wire brush / comb. Edges of repair areas of belts, hoses, tyres etc. should be undercut. All loose dust and particles should be blown clear of the prepared surface. On certain repairs such as gaskets and castings where one surface is not required to bond to the Scotchkote Urethane Elastomer 80FG 532, these surfaces should be treated with 3M™ Scotchkote™ Release Agent 035.

### Priming

All areas to be repaired or resurfaced should be first primed with 3M™ Scotchkote™ Urethane Elastomer Primer 075. The primer should be applied with a soft bristled brush to give an even, but low coating thickness, taking care to avoid ponding of the primer.

The primer should be allowed a minimum of 60 minutes and a maximum of 8 hours at 20°C (68°F) before applying Scotchkote Urethane Elastomer 80FG 532.

### Product Mixing

Scotchkote Urethane Elastomer 80FG 532 is a two component material which must be mixed together prior to use.

The contents of the base container should be transferred to the mixing container provided. The contents of the activator should be added to the base with continuous stirring to produce a streak free viscous liquid. Where less than full unit mixes are required it is essential that the product be mixed accurately weighing out the quantities of base and activator.

Thorough mixing is extremely important, and once the material appears mixed, a further period of mixing should be carried out to ensure there is no unmixed material. The mixed material should be used within 20 minutes of mixing at 20°C (68°F).

### Application Procedures

For casting / moulding the mixed product should be poured into the prepared mould, the filled mould should be gently vibrated to aid the release of trapped air. All equipment must be cleaned immediately after use with a suitable degreasing agent. If your local air quality regulations allows its use, we recommend using 3M Scotchkote Universal Cleaner 020.

### Properties

Property	Value
Color	Black
Ratio	1:1.4 By volume 3:4 By weight
<b>Drying &amp; Cure times at 20°C (68°F)</b>	
Useable life	15 mins
Initial Set	1 hour
Machining	16 hours
Full Mechanical	3 Days
Volume Solids	100%
V.O.C (As Supplied)	0 g/L
Volume Capacity	933 cc (57 cu ins) per kilo
Tensile Strength	7 Mpa (1000 psi)
Dielectric Strength	16 KV/mm (406 V/mil)
Elongation	500%
Shore A Hardness	80
Shore A Hardness	80



## Packaging and Storage

Supplied in 0.50 and 2.0 kilo packs

Use within 12 months of purchase. Store in original sealed containers at temperatures between 5°C (40°F) and 30°C (86°F).

## Handling and Safety Precautions

Read all Health Hazard, Precautionary and First Aid, Material Safety Data Sheet, and/or product label prior to handling or use.

## Ordering Information/Customer Service

For ordering technical or product information, or a copy of the Material Safety Data Sheet, call:

Phone: 800/722-6721 or 651/575-5842

Fax: 877/601-1305

3M and Scotchkote are trademarks of 3M Company.

## Important Notice

All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product which are not contained in 3M's current publications, or any contrary statements contained on your purchase order shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.

## Warranty; Limited Remedy; Limited Liability.

Because conditions of product use are outside of our control and vary widely, the following is made in lieu of all express or implied warranties: this product will conform to 3M's published product specifications and be free from defects in material and manufacture on the date of your purchase. **3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** If this product is defective upon your receipt, your exclusive remedy shall be, at 3M's option, to replace the 3M product or refund the purchase price of the 3M product. **Except where prohibited by law, 3M will not be liable for any indirect, special, incidental or consequential loss or damage arising from this 3M product, regardless of the legal theory asserted.**



## Corrosion Protection Products Division

6801 River Place Blvd.  
Austin, TX 78726-9000  
[www.3M.com/corrosion](http://www.3M.com/corrosion)

Please recycle. Printed in USA.  
© 3M 2012. All rights reserved.  
80-6111-8555-6-A